

Technical Data Sheet

Style K902SE
50.4% Woodpulp – 49.6% PET
Creped Smooth Embossed
Turquoise

TYPICAL MATERIAL PROPERTIES

TEST	ORIENTATION	UNITS	TARGETS	METHODS
Basis Weight		g/m ²	53	WSP 130.1
Thickness		mm	0.44	WSP 120.6
Absorption Capacity		%	623	WSP 10.1
Extrinsic absorption capacity		ml/m ²	348	WSP 10.2
Grab Tensile Strength	MD	N/4in	110	ASTM D5034
	CD	N/4in	56	ASTM D5034
Strip Tensile Strength	MD	N/5cm	107	WSP 110.4
	CD	N/5cm	38	WSP 110.4

WSP = Worldwide Strategic Partners: Standard Test Methods for the Nonwoven Industry

Glatfelter Sontara Asturias S.A.U

Technical Data Sheet to be revised annually. Results provided are measured with internal procedures inspired by the quoted norms if applicable. Minimum and maximum values are average and not individual results. These are not specifications and only to be used as indicative properties. All properties are typical values according to our current knowledge at the time of the last update of this publication. They are given for general guidance only. MD = machine direction, CD = cross direction. Magnera does not warrant any results and assumes no obligation or liability whatsoever in connection with this information. Please conduct your own tests to ensure consistency for your applications. The publication of these properties does not grant any right or license to any intellectual property of Magnera. Data last updated Jun 11, 2024 ©2024 A Magnera Corporation. All rights reserved.